

C-Lite Technical Data

C-Lite Cured	
Impact Strength	22.0±3.16 J/m
Young's Modulus	2.3±0.1 GPa
Yield Strength	43.8±2.6 MPa
Ultimate Tensile Strength	64.7±3.0 MPa
Elongation at Break	3.2±0.5%
Surface Resistivity	10 ⁶ Ω
Flexural Stress	156±12 MPa
Flexural Modulus	16±0.4 GPa
Flexural Strain	1%
Deflection Temperature	250° C

